

STANDARD

**STYLE 2110**  
**HIGH PERFORMANCE**  
**10-oz. FABRIC**  
**Typical Properties**

Unless stated otherwise, values presented represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.

*Issued October 2002*

Base Fabric Type	Nylon
Base Fabric Weight (nominal)	5.0 oz/yd <sup>2</sup>
Finished Coated Weight	10 oz/yd <sup>2</sup>
ASTM D751	+2/-1 oz/yd <sup>2</sup>
Tongue Tear	8" x 10" sample @ 12"/min
ASTM D751	80/80 lb <sub>f</sub>
Grab Tensile	350/300 lb <sub>f</sub>
ASTM D751	
Strip Tensile	300/275 lb <sub>f</sub> /in
ASTM D751 Procedure B	
Adhesion	7 lb <sub>f</sub> /in
ASTM D751 Dielectric Weld	
Low Temperature	1/8 in mandrel, 4 hr
ASTM D2136	Pass @ -40° F
Hydrostatic Resistance	250 psi
ASTM D751 Procedure A	
Flame Resistance	Sample not consumed within 2
FTMS 191-Method 5910	minutes