

STANDARD

STYLE 2114
HIGH PERFORMANCE
14-oz. FABRIC
Typical Properties

Unless stated otherwise, values presented represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.

Issued October 2002

Base Fabric Type	Nylon
Base Fabric Weight (nominal)	5.0 oz/yd ²
Finished Coated Weight	14 oz/yd ²
ASTM D751	+2/-1 oz/yd ²
Tongue Tear	8" x 10" sample @ 12"/min
ASTM D751	80/80 lb _f
Grab Tensile	350/300 lb _f
ASTM D751	
Strip Tensile	
ASTM D751 Procedure B	300/275 lb _f
Adhesion	
ASTM D751 Dielectric Weld	10 lb _f /in
Low Temperature	1/8 in mandrel, 4 hr
ASTM D2136	Pass @ -40° F
Hydrostatic Resistance	
ASTM D751 Procedure A	350 psi
Flame Resistance	Sample not consumed
FTMS 191-Method 5910	within 2 minutes