

STANDARD

STYLE 3022
HIGH PERFORMANCE
22-oz. FABRIC
Typical Properties

Unless stated otherwise, values presented represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.

Issued October 2002

Base Fabric Type	Nylon
Base Fabric Weight (nominal)	6.0 oz/yd ²
Finished Coated Weight	22.0 oz/yd ²
ASTM D751	+2/-1 oz/yd ²
Tongue Tear	8" x 10" sample @ 12"/minute
ASTM D751	150/150 lb _f
Grab Tensile	500/500 lb _f
ASTM D751	
Strip Tensile	
ASTM D751 Procedure B	400/325 lb _f /in
Adhesion	
ASTM D751 Dielectric Weld	10 lb _f /in
Hydrostatic Resistance	
ASTM D751 Procedure A	500 psi
Low Temperature	1/8 in mandrel, 4 hr
ASTM D2136	LTC: Pass @ -40° F LTA: Pass @ -67° F
Flame Resistance	Sample not consumed
FTMS 191-Method 5910	within 2 minutes