

**STANDARD**

**STYLE 8207**  
**HIGH PERFORMANCE**  
**7-oz. MESH**  
**Typical Properties**

Unless stated otherwise, values presented represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.

*Issued October 2002*

Base Fabric Type	Polyester
Base Fabric Weight (nominal)	3.0 oz/yd <sup>2</sup>
Finished Coated Weight	7 oz/yd <sup>2</sup>
ASTM D751	+2/-1 oz/yd <sup>2</sup>
Tongue Tear	8" x 10" sample @ 12" /min
ASTM D751	100/100 lb <sub>f</sub>
Grab Tensile	230/200 lb <sub>f</sub>
ASTM D751	
Strip Tensile	200/140 lb <sub>f</sub> /in
ASTM D751 Procedure B	
Low Temperature	1/8 in mandrel, 4 hr
ASTM D2136	Pass @ -40° F
Flame Resistance	Sample not consumed within 2 minutes
FTMS 191-Method 5910	